



COLLAK, S.A. – C/. França, 3 – Pol. Ind. Pla de Llerona – 08520 Les Franqueses del Vallès – NIF A08344897 Tel.: (+34) 93 849 44 33 – Fax: (+34) 93 849 22 77 – E-mail: <u>collak@collak.com</u> – <u>www.collak.com</u>

MS-CRISTAL TDS v1.0 06/19

COLLAK TOT-MS CRISTAL Transparent MS-Polymer adhesive sealant

1. DESCRIPTION

One component totally elastic transparent moisture curing adhesive and sealant based on MS-Polymer.

Silicone, isocyanates and solvent free. Good ageing properties and permanently elastic. No attack or corrosion of metals. Very good paint compatibility with most industrial paints, lacquer and coating systems. Odourless and easily extrudable. Not suitable for areas exposed to direct solar radiation.

2. APPLICATION

Good adhesion without need of primer on: iron, galvanised, aluminium, copper, brass, stainless steel, zinc, etc. Also suitable for uPVC, epoxy, polyester, concrete, ceramics, glass, glazed surfaces, melamine, wood, lacquered wood, etc. No adhesion on polyethylene and Teflon (PTFE). Adhesion on humid surfaces. Resistant to hits and vibrations. Suitable as DIY adhesive-sealant and high transparency household repairs. Use only indoors.

TECHNICAL DATA			
DELIVERY FORM:		CURED PRODUCT:	
Basic material:	MS-Polymer	Hardness Shore A	$25\pm5~^{(3)}$
Specific weight:	1,03 g/ml	Elongation at break:	> 200 % ⁽²⁾
Consistency:	Thixotropic paste.	E-modulus (100%):	$0.70 \pm 0.10 \text{ N/mm}^2 \text{ (Mpa)}^{(2)}$
Application temperature:	+ 5 to + 50 °C.	Tensile at break:	> 1.0 N/mm² (Mpa) ⁽²⁾
Character	Elastic.	Tack-free:	25-30 Min. ⁽¹⁾
Colours:	Transparent, Colourless	Volume change after 2 hours	3%
Easy to extrude and odourless. Can be painted.		Temp. resistance: Temp. resistance SHORT:	-30°C to + 90°C + 110 °C

(1): 23°C, 50 %HR

⁽²⁾: According DIN 53504

⁽³⁾: According DIN 53505

3. INSTRUCTIONS FOR USE

The surfaces to fix / seal should be firm, dry, clean and free from dust or grease. Before usage, tests are recommended to ensure the suitability of the product for its application. In open joints, TOT-MS Cristal can be smoothened / tooled with a spatula moistened in soapy water if necessary.

4. PACKING

300 ml. transparent cartridges (12 cartridges / carton).

5. STORAGE

Can be stored for 12 months in closed (unopened) container in a dry place at temperatures between +5°C and +30°C.

6. CAUTIONS

No specific safety precautions required. Consult safety data sheet. Apply the usual industrial hygiene. Avoid any contact with skin and eyes. If swallowed, consult a physician. Keep away from children.





COLLAK, S.A. – C/. França, 3 – Pol. Ind. Pla de Llerona – 08520 Les Franqueses del Vallès – NIF A08344897 Tel.: (+34) 93 849 44 33 – Fax: (+34) 93 849 22 77 – E-mail: <u>collak@collak.com</u> – <u>www.collak.com</u>

Every endeavour has been made to ensure that the information given herein is true and reliable, but is given only for the guidance of our customers. Collak, S.A. cannot accept any responsibility for loss or damage or infringements of patent rights that may result from the use of the information, due the possibility of variations of processing or working conditions are outside our control. Users are advised to confirm the suitability of the products with their own tests. Our technical service is at customer's disposal for any conference, explanation or advise.