



# COLLAK, S.A. – C/. França, 3 – Pol. Ind. Pla de Llerona – 08520 Les Franqueses del Vallès – NIF A08344897

01/24-SUPERCOLLAK-v1.0

# **SUPERCOLLAK**

Tel.: (+34) 93 849 44 33 - Fax: (+34) 93 849 22 77 - E-mail: collak@collak.com - www.collak.com

#### 1. DESCRIPTION

Cyanoacrylate adhesive that cures spontaneously and rapidly in contact with a wide range of materials developing high resistance unions.

#### 2. APLICATION

Universal cyanoacrylate adhesive excellent to use with most of the materials employed in construction market such as metals, wood, ceramics, plastics, rubber, etc.

#### 3. INSTRUCTIONS FOR USE

Surfaces to adhere should be firm, consistent (sound), clean and free from dust and grease.

Apply adhesive only on one of the surfaces. Assembly and press during some seconds.

Good assembling quality is reached using the minimum quantity of adhesive. An excessive use can lead to deficient or failed assemblies.

Speed of the union depends on the gap and humidity content: less gap and higher humidity better to accelerate the adhesion process.

Times needed to get a good adhesion:

Metal/Metal: < 25 seconds</li>
Plastic/Plastic: < 10 seconds</li>
Rubber/Rubber: < 5 seconds</li>

# **5. TECHNICAL DATA**

Colour: Transparent Density: 1.06 g/ml

Maximum Gap fill: 0.15 mm

Temperature range: -50°C to +80°C.

## **6. PACKAGING AND STORAGE**

Shelf life of the adhesive is 12 months stored in a fresh and dry place avoiding direct UV exposition. Storage in a fridge can increase shelf life of this product.

## 7. PRODUCT SAFETY

Irritant product. Avoid contact with eyes and skin. For more information see material safety data sheet.

All data and recommendations given in this Product Data Sheet are given in good faith and based upon information, which we believe to be reliable, but they are made without any representation of guarantee or warranty or accuracy and are made with reservation of all rights. We reserve the right to modify specifications at all times. User should be aware of the current developments of the above-mentioned product. No liability regarding application or circumstances during application can be accepted.